

IBERINOX 88



TUNGSTEN ALLOYS

	W	NI	Co	Fe	Ta	Cu	C	Others
Densalloy	96	2,00		2,00				
Tungsten Carbide I	Balance		6,00				7	8 TIC
Tungsten Carbide II	Balance		8,50				5	
Tungsten Carbide III	Balance		10				5	
Other tungsten Carbide	Balance	5-15	10-30		8 TaC		6	