

CLASIFICACIÓN ALEACIONES NÍQUEL/CROMO/MOLIBDENO

	Ni	Cr	Mo	W	Fe	Al	Ti	Cu	Nb	Otros
HASTELLOY B	62	1	28		5,50					2,5 Co
HASTELLOY C-22	54	21	14	3	5	0,40				2,5 Co
HASTELLOY C-276	56	16	17	4	5,50	0				
HASTELLOY G	44	22	6,50	1	20			2	2	
HASTELLOY R	66	15,50	5		7	2,20	2,50			1,5 Co
HASTELLOY S	68	15,50	15		1					
HASTELLOY X	47	22	9	0,60	18,50					1,5 Co
INCO 600	75,50	15,50			7,00					
INCO 625	61	21,50	9		3				3	
INCO 718	53	18,50	3		18				5	
INCO 800	32	20			47					
INCO 825	40	21	3		32		1,00	2		